

220132	NC White Topcoat 132 MT
--------	-------------------------

Matt Nitrocellulose Topcoat White

FEATURES

Properties	Silky touch	Quick drying	Good opacity
Recommended use	Indoor woodwork	Interior Doors	All kind furniture
Application method	Spray gun	Airmix gun	
Recommended Hardeners			
Diluyentes Recs.	5520201	520204 Medium Retardant	540414 Retarder solvent

AVAILABLE GLOSSES

220132	19 - 24% (60°)		

TYPICAL DATA (25 °C)

Supply Viscosity, DIN4 (s)	25 - 35		
Density (g/cm³)	1,04 - 1,08		
Solid content (%)	35 - 39		
VOC content (%weight):	62,45		

GENERAL FEATURES

Drying 120 g/m² at 25°C			
Dust-free drying of 120 g/m² (min)	5 - 10		
Touch-free drying of 120 g/m² (min)	20 - 25		
Stackable	24 h		
Recoating	18 h after sanding		
Recommended Weight (g/m²)	130 - 150		

SUBSTRATE PREPARATION

Apply over appropriate sealer. Sealer must be sanded with 320-400 sand paper before the topcoat application in order to get a perfect adherence. Make sure that the surface is clean of dust or any other contaminant (grease, silicone, etc.)

APPLICATION ADVICES

The type and quantity of solvent recommended are a guide, it depends on the application system and the environmental conditions. Generally thin with 10-20 % 520201 Solvent 201 Nitro. At high temperatures or humidity addition of 5 - 10% of 520204 Solvent 204 Retardant Medium or 540414 Solvent 414 Retardant is recommended.

Application	% Thinner	Nozzles	Aire Pressure (Bar)	Pump Pressure (Bar)
Spray Gun	10 - 20	1,5 - 2	2 - 4	
Airmix	5 - 15	0,6 - 0,9	1 - 3	60 - 130

PRECAUTIONS

Mix properly before using.
We recommend to apply at 15 - 25 °C and 50 -75% relative humidity.
Paint residues must be removed according to current regulations.
With regard to the danger and toxicity of this product before using it, we advise you to read its MSDS
Expiry date: 1 year (Stored between 5 - 35 °C)

ADDITIVES

Action	ADD	Dosage %	Grams per 20 L can
Anti.Silicone Additive	980066 Anti-Silicone Additive 066	5 % Max	1000 Max
Gloss Reduce	910015 Matting Additive 015	10% Max	2000 Max

THE FIGURES IN THIS DOCUMENT SHOULD BE UNDERSTOOD AS A GUIDANCE AND NOT AS A SALES SPECIFICATION.

Note: The aforementioned data and the advices we give verbally, in writing or through tests, have been carried out following our loyal knowledge and mind, nevertheless they are considered as mere advices and indications without any obligation, and also with regard to the possible third party industrial property rights. Our advice does not exempt you from doing tests to the indications we may give you or to the products we may provide you, in order to check if these products are the suitable for the purposes indicated. The application, use and transformation of our products and of the products you manufacture under our technical advice will be made out of our vigilance and therefore will be of your sole responsibility. The sale of our products is under our Selling and Delivery General Conditions. **23-06-2022_Version-1**

VALRESA. Polígono Industrial Reva
Avda. dels Gremis, s/n Sector 13
Riba-Roja de Turia Valencia E46394
ESPAÑA Tel. 96 1669560