

270018

Esfera White Sealer 0018

Interior Water based White Sealer

FEATURES

Properties	Good covering	Quick drying	Smooth sanding
Recommended use	Interior general use	MDF Board	Rustic
Application method	Spray Gun Cup	Airmix system	
Recommended Hardeners			
Diluyentes Recs.	Water		

AVAILABLE GLOSSES

TYPICAL DATA (25 °C)

Suply Viscosity DIN 6 (s)	30 - 50		
Density (g/cm ³)	1,290 - 1,320		
Solid content (%)	53 - 57		
VOC contents (% Weight)	2,50		

GENERAL FEATURES

Drying conditions at 25°C		Tunel drying		
Dust-free (min)	10 - 15	Flash Off	25°C	2 - 5 min
Touch-free (min)	30 - 40	Laminar Flow Area	40 - 45 °C	15 - 20 min
Stackable	24 hr	Cooling		10 min
Sanding / Overcoating	3 - 4 hr	Spreading rate (m ² /L)	10 - 15	
Recomended Weight (g/m ²)	120 - 160			

SUBSTRATE PREPARATION

Sand the surface previously with 180 - 220 sand paper. Make sure the surface is clean of dust or any other contaminant (grease, silicone, etc.). The sanding and drying will improve if we apply a temperature of 35 - 40°C during drying time.

APLICACION ADVICES

Ready to use product. It is recommended to apply at temperature between 20 to 25°C and relative humidity of 45 to 75%. Every tool used should be made of stainless steel. They should be clean immediately with water or appropriate solvents. Air renovation is necessary 3/4 times per hour in drying chambers.

Application	% Thinner	Nozzles	Aire Pressure (Bar)	Pump Pressure (Bar)
Spray Gun	20 - 25	2- 2,5	2,5 - 3	
Airmix	20 - 25	09 - 11	0 - 2	40 - 120

PRECAUTIONS

Mix properly before using.
Paint residues must be removed according to current regulations.
With regard to the danger and toxicity of this product before using it, we advise you to read its MSDS
Expiry date: 1 year (Storage between 5-35 °C)

ADDITIVES

Action	ADD	Dosage %	Grams per 20 L can
Retarder Drying	980903 Retardant Additive	2 Máx	400 Máx
Antifoaming	980909 Antifoaming Additive	0,5 - 1	100 - 200

THE FIGURES IN THIS DOCUMENT SHOULD BE UNDERSTOOD AS A GUIDANCE AND NOT AS A SALES SPECIFICATION.

Note: The aforementioned data and the advices we give verbally, in writing or through tests, have been carried out following our loyal knowledge and mind, nevertheless they are considered as mere advices and indications without any obligation, and also with regard to the possible third party industrial property rights. Our advice does not exempt you from doing tests to the indications we may give you or to the products we may provide you, in order to check if these products are the suitable for the purposes indicated. The application, use and transformation of our products and of the products you manufacture under our technical advice will be made out of our vigilance and therefore will be of your sole responsibility. The sale of our products is under our Selling and Delivery General Conditions. **29-04-2022_Version-3**

VALRESA. Polígono Industrial Reva
Avda. dels Gremis, s/n Sector 13
Riba-Roja de Turia Valencia E46394
ESPAÑA Tel. 96 1669560