

270200

ESFERA Nat Effect Self-Sealer 0200 SMMT

Natural Water based extra matt Self-Sealer with excelent scratch resistance

FEATURES

Properties	Scratch resistance	Natural aspect	Deep matt but very transparent
Recommended use	For any tipe of furniture	Open pore process. Solid wood	Contract, Rustic style, designer furniture
Application method	Cup spray Gun	Airmix system	
Recommended Hardeners	5:1 190200		
Diluyentes Recs.	Water		

AVAILABLE GLOSSES

270200	3 - 5% (60º)		

TYPICAL DATA (25 °C)

Suply Viscosity DIN 6 (s)	55 - 80		
Density (g/cm³)	1,030 - 1,080		
Solid content (%)	30 - 35		
VOC contens (% Weight)	2,00		

GENERAL FEATURES

Drying conditions at 25°C			
Dust-free (min)	60		
Touch-free (min)	120		
Stackable	> 24 h		
Sanding / Overcoating	> 24 h		
Recomended Weight (g/m²)	80 - 100		

SUBSTRATE PREPARATION

It is recommended sanding surfece previously with 180 - 220 sand paper. Make sure the surface is clean of dust or any other contaminant (grease, silicone, etc.). Sand softly and recoat with the same product
The sanding and drying will improve if we apply a temperature of 35 - 40°C during drying time.

APLICACION ADVICES

Mix properly with hardener and wather (25 - 35%).
It is recommended to apply al temperature between 20 to 25°C and relative humidity of 45 to 75%
Air renovation is necessary 3/4 times per hour inn drying chambers. Every tool used should be made of stanless stel. They should be clean inmediatly with water or appropriate solvents

Aplication	% Thinner	Nozzles	Aire Pressure (Bar)	Pump Pressure (Bar)
Spray Gun	25 - 35	1,5- 2	2,5 - 3	
Airmix	25 - 35	06 - 11	0,5 - 2	40 - 120

PRECAUTIONS

Mix properly before using.
Paint residues must be removed according to current regulations.
With regard to the danger and toxicity of this product before using it, we advise you to read its MSDS
Expiry date: 1 year (Storage between 5-35 °C)

ADDITIVES

Action	ADD	Dosage %	Grams per 20 L can

THE FIGURES IN THIS DOCUMENT SHOULD BE UNDERSTOOD AS A GUIDANCE AND NOT AS A SALES SPECIFICATION.

Note: The aforementioned data and the advices we give verbally, in writing or through tests, have been carried out following our loyal knowledge and mind, nevertheless they are considered as mere advices and indications without any obligation, and also with regard to the possible third party industrial property rights. Our advice does not exempt you from doing tests to the indications we may give you or to the products we may provide you, in order to check if these products are the suitable for the purposes indicated. The application, use and transformation of our products and of the products you manufacture under our technical advice will be made out of our vigilance and therefore will be of your sole responsibility. The sale of our products is under our Selling and Delivery General Conditions. **01-08-2022_Version-3**

VALRESA. Polígono Industrial Reva
Avda. dels Gremis, s/n Sector 13
Riba-Roja de Turia Valencia E46394
ESPAÑA Tel. 96 1669560