

310100

CV White Sealer 100

2 k acid cured white prime (or post cat primer)

FEATURES

Properties	Excellent filling of pores	Excellent leveling	Easy sanding
Recommended use	High quality furniture	Flat & vertical	
Application method	Airmix	Conventional spray gun	
Recommended Hardeners	10:1 390001		
Diluyentes Recs.			

AVAILABLE GLOSSES

TYPICAL DATA (25 °C)

Viscosity DIN 6 (s)	25-35	COV (weight %)	46%
Mix Viscosidad (s)	15-21	Pot life	> 8 h
Density (g/cm3)	1,210		
Solid content	54%		

GENERAL FEATURES

Dust free	15 min		
Touch free	30-40 min		
Sandability	> 6h		
Stacability	>12 h (según peso)		
Packable	48 h		

SUBSTRATE PREPARATION

Applied over sanded pieces (180 sand paper)
Make sure substrate is completely free of dust or any contaminant

APLICACION ADVICES

Mix 10 :1 with 390001 CV Catalyst 00. Dilute 20-30 % with thinner when neccessary. Apply 120-160 g/m2

PRECAUTIONS

During drying time, air currents must be avoided, because they will dry the surface of the film, appearing such problems like deaeration and inappropriate levelling
With regard to the danger and toxicity of this product before using it, we advise you to read its MSDS
We recommend to keep the product at a temperature between 5 and 35°C, avoiding direct sun exposures of the containers.
Expiry date: 1 year

ADDITIVES

THE FIGURES IN THIS DOCUMENT SHOULD BE UNDERSTOOD AS A GUIDANCE AND NOT AS A SALES SPECIFICATION.

Note: The aforementioned data and the advices we give verbally, in writing or through tests, have been carried out following our loyal knowledge and mind, nevertheless they are considered as mere advices and indications without any obligation, and also with regard to the possible third party industrial property rights. Our advice does not exempt you from doing tests to the indications we may give you or to the products we may provide you, in order to check if these products are the suitable for the purposes indicated. The application, use and transformation of our products and of the products you manufacture under our technical advice will be made out of our vigilance and therefore will be of your sole responsibility. The sale of our products is under our Selling and Delivery General Conditions. **25-05-2023_Version-1**

VALRESA. Polígono Industrial Reva
Avda. dels Gremis, s/n Sector 13
Riba-Roja de Turia Valencia E46394
ESPAÑA Tel. 96 1669560